

LENNTECH

info@lennotech.com
www.lennotech.com
Tel. +31-152-610-900
Fax +31-152-616-289

Features and Benefits

- High activity
- Optimum pore size distribution
- Water washed
- Low dust
- High hardness
- Good abrasion resistance
- Proven superior for multiple reactivations
- Excellent adsorption capacity
- Both adsorption and transport pores

Typical Applications

- Treatment of municipal drinking water
- Production of soft drinks and beer
- Treatment of residential water
- Adsorption of taste and odor
- Protection of ion exchange resins

Available Particle Sizes

- 20x50 mesh (0.30 - 0.85 mm)
- 12x40 mesh (0.425 - 1.70 mm)
- 8x30 mesh (0.60 - 2.36 mm)
- 8x16 mesh (1.18 - 2.36 mm)
- 6x12 mesh (1.70 - 3.35 mm)

Certifications and Approvals

- ANSI / NSF standard 61
- AWWA B604-96
- EN12915
- Food and water codex

Standard Packaging

- 25 kg bag (55 lb)
- 500 kg bulk bag (1100 lb)



The polyethylene valve bag from Jacobi sets the standard in the industry for clean, durable and safe handling.

AquaSorb® 1500

granular coal based activated carbon

AquaSorb® 1500 is a high activity granular activated carbon manufactured by steam activation from select grades of bituminous coal. The perfect balance between adsorption and transport pores provides optimum performance in a wide range of water treatment applications. The product is a high density adsorbent and provides maximum volume activity. The material is water washed during manufacture and therefore wets rapidly. The excellent hardness and mechanical strength ensures negligible losses during backwashing, air scouring and multiple reactivations.



Soft drink manufacturers and breweries rely upon AquaSorb® activated carbon for dechlorination and dissolved organic removal.

Specification

| | |
|-------------------|---------------|
| Iodine number | min. 950 mg/g |
| Moisture content | max. 5% |
| Total ash content | max. 15% |
| Wettability | min. 95% |
| Hardness | min. 95% |

Typical Properties

| | |
|-----------------------|-------------------------|
| Surface area | 1000 m ² /g |
| Methylene blue number | 240 mg/g |
| Total pore volume | 0.99 cm ³ /g |
| Water soluble ash | 0.2% |
| Apparent density | 495 kg/m ³ |
| pH | 8-11 |

Jacobi Carbons reserves the right to modify specifications without prior notice. To obtain a full sales specification with test methods, please contact your nearest Jacobi Carbons office.



Jacobi
THE CARBON COMPANY

LENNTECH

info@lennotech.com Tel. +31-152-610-900
www.lennotech.com Fax. +31-152-616-289



Certified to ANSI/NSF Std. 61



Polyethylene valve bags of
25 kg (55 lb) net weight on
500 kg (1100 lb) pallets



Polypropylene liner-free
FIBCs (super sacks) of
500 kg (1100 lb) net weight

CAUTION Activated carbon is a strong oxidizing agent and can remove oxygen from air under wet or humid conditions. Care should be taken when entering confined spaces where wet activated carbon is present. Ensure the use of correct breathing apparatus. Material Safety Data Sheets should be consulted for further details on procedures in the event of contact with activated carbon.

NOTICE Due to the progressive nature of Jacobi Carbons Group and the continually improving design and performance of our products, we reserve the right to change product specifications without prior notification. The information contained in this datasheet is intended to assist a customer in the evaluation and selection of products supplied by Jacobi Carbons. The customer is responsible for determining whether products and the information contained in this document are appropriate for customer's use. Jacobi Carbons assumes no obligation or liability for the usage of the information in this datasheet, no guarantees or warranties, expressed or implied, are provided. Jacobi Carbons disclaims responsibility and the user must accept full responsibility for performance of systems based on this data.

ISO 9001

BUREAU VERITAS
Certification

